

Cartilage tensile test:

1. Sample taken from deep zone.
2. 10g find contact load (for initial length)
3. 10k load cell.
4. Protocol: find contact->preconditioning->find contact->stress relaxation.
5. 1000 preconditioning cycles.

oks00TR2-FMC-McuX-02-01 length: 6.428 mm (for preconditioning), 6.5410 mm (for stress relaxation).
oks00TR2-FMC-McuX-02-02 length: 6.5115 mm (for preconditioning), 6.5800 mm (for stress relaxation).
oks00TR2-FMC-McuX-02-02 length: 6.5425 mm (for preconditioning), 6.6145 mm (for stress relaxation).

