

Cartilage tensile test

1. thickness=0.388 mm
2. Protocol: initial length-> preconditioning->initial length-> stress relaxation
3. 1000 preconditioning cycles (upto 15% strain)

oks00TR2-FMC-MCuX-03-01 lengths: 6.3345 (for preconditioning), 6.4720 (for stress relaxation)

oks00TR2-FMC-MCuX-03-02 lengths: 6.4615 (for preconditioning), 6.5445(for stress relaxation)

