

oks00TR2-QAT-CXXX-10-01/02/03: tendon tensile test. used wet cotton gauze to wrap the end of sample and glued to both sides of clamp. **2000 preconditioning cycles** (except for SR protocol, image acquisition was every 10s, 0.1s for SR.) 4.5 % max strain, 10%/S strain rate . 01 positions: 6.8205, 6.9845 ; 02 positions: 6.9875, 7.0855; 03 positions: 7.0485, 7.1265

