

Cartilage unconfined compression test:

1. 10g find contact load
2. 10k load cell.
3. Protocol: find contact->preconditioning->find contact->stress relaxation.
4. 1000 preconditioning cycles.
5. Thickness: 3.5439 mm.
6. sample tends to float away from its initial position in preconditioning.

oks00TR2-TBC-LCXX-01-01 indenter position: 91.0415 (for preconditioning), 91.0700 (for stress relaxation)

oks00TR2-TBC-LCXX-01-02 indenter position: 91.0055 (for preconditioning), 91.0565 (for stress relaxation)

oks00TR2-TBC-LCXX-01-03 indenter position: 91.0255 (for preconditioning), 91.0870 (for stress relaxation)

