

oks00TR5-rubber2-01/02: rubber unconfined compression test. thickness:1.405 mm. preconditioning with ramp before and after. 15% strain at 5%/s. 5-10-15 % strain at 5%/s. preconditioning 10-15% strain at 0.5Hz. 01 positions: 25.2375,25.2445 ; 02 positions: 25.243,25.2465.

oks00TR5-rubber2-03/04: rubber unconfined compression test. thickness:1.405 mm. preconditioning with ramp before and after. 15% strain at 5%/s. 5-10-15 % strain at 5%/s. preconditioning 10-15% strain at 0.5Hz. 03positions: 25.6415,25.6465 ; 04 positions: 25.6445,25.647.



