

oks00TR6-TBC-MCXX-02-01/02: cartilage unconfined compression. thickness:1.96 mm. full tests (with 30 min hold). no ramps before and after preconditioning . 5-10-15 % strain at 20%/s. 1000 preconditioning cycles at 2hz (10-15% strain). 01 positions: 42.4655,42.64; 02 positions: 42.538,42.6715. (PBS used instead of saline, all protocols were already updated before test started, cartilage strip had thawed by the time sample was taken out)

oks00TR6-TBC-MCXX-02-03/04: cartilage unconfined compression. thickness:2.00 mm. full tests (with 30 min hold). no ramps before and after preconditioning . 5-10-15 % strain at 20%/s. 1000 preconditioning cycles at 2hz (10-15% strain). 03 positions: 46.8095,46.957; 04 positions:46.8095,46.9495. (PBS used instead of saline, all protocols were already updated before test started, cartilage strip had thawed by the time sample was taken out)

oks00TR6-TBC-MCXX-02-05: cartilage unconfined compression. thickness:2 mm. full tests (with 30 min hold). no ramps before and after preconditioning . 5-10-15 % strain at 20%/s. 1000 preconditioning cycles at 2hz (10-15% strain). 05 positions 55.8485,55.9515(PBS used instead of saline, all protocols were already updated before test started, cartilage strip had thawed by the time sample was taken out)

