

Day 1:

oks00TR5-rubber3-01/02: rubber unconfined compression test. thickness:1.68 mm. preconditioning with ramp before and after. 15% strain at 20%/s. 5-10-15 % strain at 20%/s. preconditioning 10-15% strain at 2Hz. 01positions: 45.7275,45.7315; 02 positions:45.7260,45.7330. One hour rest between two tests.

Day 2:

oks00TR5-rubber3-03/04: rubber unconfined compression test. thickness:1.68 mm. preconditioning with ramp before and after. 15% strain at 20%/s. 5-10-15 % strain at 20%/s. preconditioning 10-15% strain at 2Hz. 01Positions: 27.0095, 27.0155. 02 positions: 27.0125, 27.0065

Sample source: Unknown

